

Lexan* HPxxE Film

Product Datasheet

Description

Lexan HPXXE graphic films are high-performance coated films offering excellent chemical and highest abrasion resistant package of any films in the SABIC Innovative Plastics graphic film product line. Features include: Extreme durability of coating, 1/8" Mandrel bend flexibility, Gouge resistance, excellent clarity and consistency of gloss level.

Note: Lexan HPXXE film cannot be first surface printed with graphics or textures and it is not suggested for 3D forming.

Typical Property Values♦

Property	ASTM Test Method	Units (USCS)	Value	ISO Test Method	Units (SI)	Value
Mechanical						
Tensile Strength						
@ Yield	ASTM D882	psi	8800	ISO 527	MPa	60
Ultimate	ASTM D882	psi	9000	ISO 527	MPa	62
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.51	ISO 34	kN/m	264
Propogation	ASTM D1922	g/mil	40		kN/m	14
Thermal						
Vicat Softening Temperature, B	ASTM 1525	°F	320	ISO 306	°C	160
Heat Deflection Temp. by TMA at 1.8 Mpa		°F	290	ISO 75 Modified	°C	145
Shrinkage at 302°F (150°C)	ASTM D1204	%	1.40%			1.40%
Brittleness Temperature	ASTM D746	°F	-211		°C	-135
Physical						
Density	ASTM D792	slug/ft ³	2.3	ISO 1183	kg/m ³	1200
Pencil Hardness	ASTM D3363	-	HB			
Taber Abrasion	ASTM D1044	delta Haze	3-4			
Optical						
Refractive Index @77°F (25°C)	ASTM D542A	-	1.5			
Light Transmission	ASTM D1003	%	92			
Yellowness Index	ASTM D1925	%	0.7			
Haze	ASTM D1003	%	0.5			

- ♦ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC Innovative Plastics representative or the SABIC Innovative Plastics Quality Services Department. Reported Values are Based on 0.010" (0.250 mm) Thickness unless otherwise noted.
- * Trademark of SABIC Innovative Plastics IP BV

Lexan* HPxxE Film Product Datasheet

Manufacturing Specifications

Nominal Gauge Ranges	Min./Max Limit of Nominal
0.007" (0.175mm)	-10% / +24%
0.010" (0.250mm)	-10% / +20%
0.015" (0.375mm)	-5% / +12%
0.020" (0.500mm)	-5% / +10%

Chemical Resistance

Chemical	Results
One Hour Continuous Surface Contact at 73° F	
Acetone	Passed
MEK	Passed
Toluene	Passed
Methylene Chloride	Passed
Isopropyl Alcohol	Passed
Cyclohexane	Passed
EthylAcetate	Passed
40% NaOH	Passed
Conc.HCL	Passed
Gasoline (Unleaded)	Passed
Butyl Cellosolve	Passed



* Trademark of SABIC Innovative Plastics IP BV

¹ Failure constitutes any of the following: non-removable stain or cloudiness, blistering, delamination, or cracking of the coating or failure to pass crosshatch tape adhesion

Americas Headquarters

SABIC Innovative Plastics
One Plastics Avenue
Pittsfield, MA 01201
USA
T +1-413-448-7125
Toll-free: 1-800-323-3783 ext.3
F +1 (888) 443-2033
sfscustomerservice@sabic-ip.com

European Headquarters

SABIC Innovative Plastics
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 164 29 2742
F +31 164 293272

Pacific Headquarters

SABIC Innovative Plastics
Specialty Film & Sheet
1266 Nanjing Road (W)
16th Floor, Plaza 66
200040 Shanghai
China
T +86 21 62881088 ext. 6733
F +86 21 6288 0818

E-mail

sfs.info@sabic-ip.com

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of SABIC Holding Europe BV

* Trademarks of SABIC Innovative Plastics IP BV

© Copyright 2011. All rights reserved.