

## Description

Lexan\* SD8B14 Film is a one side fine velvet (FV), one side fine matt (FM) clear transparent polycarbonate film that has specifically been designed to be used in government security documents, such as passport data pages, ID cards, driving licenses , ... It offers great printability and ease of processing ( laminating, die-cutting, embossing). Lexan\* SD8B14 Film is available in gauges ranging from 50 - 400µm.

## Typical Property Values◆

Property	ASTM Test Method	Units (USCS)	Value	ISO Test Method	Units (SI)	Value
<b>Mechanical</b>						
Tensile Strength @ Yield	ASTM D882	psi	8122	ISO 527	MPa	56
Ultimate	ASTM D882	psi	8122	ISO 527	MPa	56
Tensile Modulus	ASTM D882	psi	311 x10 <sup>3</sup>	ISO 527	MPa	2150
Tensile Elongation at Break	ASTM D882	%	85	ISO 527	%	85
Tear Strength						
Initiation	ASTM D1004	lbf	12	ASTM D1004	N	52
Propagation	ASTM D1938	lbf	0.6	ASTM D1938	N	2.8
<b>Thermal</b>						
Coefficient of Thermal Expansion, flow	ASTM E831	(x 10 <sup>-5</sup> / °F)	4.2	ISO 11359	(x 10 <sup>-5</sup> / °C)	7.5
Glass Transition Temperature	ASTM D3418	°F	298	ISO 11357	°C	148
Vicat Softening Temperature, B50	ASTM 1525	°F	295	ISO 306	°C	146
Heat Deflection Temp. Af 120°C/h	ASTM D648	°F	262	ISO 75 Modified	°C	128
Shrinkage at 130°C, 30min	Internal method	%	0.17	Internal method	%	0.17
<b>Physical</b>						
Density	ASTM D792	slug/ft <sup>3</sup>	2.33	ISO 1183	g/cm <sup>3</sup>	1.20
Water Absorption, 24 hrs.	ASTM D570	% change	0.09	ISO 62	% change	0.09
Surface Roughness Ra		µin	35 [FM] 91 [FV]	ISO4288	µm	0.9 [FM] 2.3 [FV]
Surface Roughness R3z		µin	165 [FM] 484 [FV]	ISO4288	µm	4.2 [FM] 12.3 [FV]
Surface Tension	Dyne solutions	Dyne/cm	44 [FM] 37 [FV]	Dyne solutions	Dyne/cm	44 [FM] 37 [FV]
<b>Optical</b>						
Light Transmission	ASTM D1003	%	87	ASTM D1003	%	87
Color: b-value	CIE Lab, Reflection, D65, 10°		1.75	CIE Lab, Reflection, D65, 10°		1.75

## Manufacturing Specifications

Nominal Gauge Ranges	Min./Max Limit of Nominal
0.050 - < 0.250 mm	± 5%
0.250 - 0.400 mm	± 2.5%

- ◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC Innovative Plastics, Specialty Film & Sheet representative or the Quality Services Department. Reported Values are Based on 0.250 mm (0.010" ) thickness film, except for the Coefficient of thermal expansion, Vicat softening temperature, Heat deflection temperature and water absorption, which are based on molded parts.

\* Trademarks of SABIC Innovative Plastics IP BV



\* Trademark of SABIC Innovative Plastics IP BV

**Americas:**

SABIC Innovative Plastics  
Specialty Film & Sheet  
One Plastics Avenue  
Pittsfield, MA 01201  
USA  
Tel. (1) (413) 448 5400  
Fax. (1) (413) 448 7506  
Toll free: 1-800 451 3147

**Europe:**

SABIC Innovative Plastics  
Specialty Film & Sheet  
Plasticslaan 1  
NL - 4612 PX Bergen op Zoom  
The Netherlands  
Tel. (31) (164) 292911  
Fax. (31) (164) 293272

**Pacific:**

SABIC Innovative Plastics  
Specialty Film & Sheet  
1468 Nanjin Road (W)  
26th Floor, United Plaza  
200040 Shanghai, China  
Tel. (86) 21 3222 4500  
Fax. (86) 21 6289 8998

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sobic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of Sabic Holding Europe BV

\* Trademark of SABIC Innovative Plastics IP BV