

Description

Lexan* SDCX50 – WH9B246 Film is a co-extruded polycarbonate film with a core Lexan*SD8B24 layer and a 50µm Lexan*SD8B94 cap-layer with a fine matte texture on both sides. This film has specifically been designed to be used in government security documents, such as passport data pages, ID cards, driving licenses and many more.

It offers great printability and ease of processing (laminating, die-cutting, hot stamping). Lexan* SDCX50 Film is available in 150µm.

Typical Property Values◆

Property	ASTM Test Method	Units (USCS)	Value	ISO Test Method	Units (SI)	Value
Mechanical						
Tensile Strength						
@ Yield	ASTM D882	psi	8265	ISO 527	MPa	57
Ultimate	ASTM D882	psi	8265	ISO 527	MPa	57
Tensile Modulus	ASTM D882	psi	348 x10 ³	ISO 527	MPa	2400
Tensile Elongation at Break	ASTM D882	%	130	ISO 527	%	130
Thermal						
Vicat Softening Temperature, B50	ASTM 1525	°F	297	ISO 306	°C	147
Shrinkage at 130°C, 30min	Internal method	%	0.17	Internal method	%	0.17
Physical						
Density	ASTM D792	slug/ft ³	2.51	ISO 1183	g/cm ³	1.29
Surface Roughness Ra (core side)		µin	16.5	ISO4288	µm	0.42
Surface Roughness Ra (cap-layer side)		µin	46.5	ISO4288	µm	1.18
Optical						
Light Transmission	ASTM D1003	%	9.40	ASTM D1003	%	9.40
Color: b-value (cap-layer side)	CIELab, Reflection, D65, 10°		-1.44	CIELab, Reflection, D65, 10°		-1.44

Manufacturing Specifications

Nominal Gauge Ranges	Min./Max Limit of Nominal
0.150 mm	± 5%

- ◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC Innovative Plastics, Specialty Film & Sheet representative or the Quality Services Department. Reported Values are Based on 0.150 mm (0.005") thickness film, except for the Vicat softening temperature which is based on molded parts.

* Trademarks of SABIC Innovative Plastics IP BV

Lexan*



* Trademark of SABIC Innovative Plastics IP BV

**Americas
Headquarters**

SABIC Innovative Plastics
One Plastics Avenue
Pittsfield, MA 01201
USA
T +1-413-448-7125
Toll-free: 1-800-323-3783 ext.3
F +1 (888) 443-2033
sfscustomerservice@sabic-ip.com

**European
Headquarters**

SABIC Innovative Plastics
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 164 29 2742
F +31 164 293272

**Pacific
Headquarters**

SABIC Innovative Plastics
Specialty Film & Sheet
1266 Nanjing Road (W)
16th Floor, Plaza 66
200040 Shanghai
China
T +86 21 62881088 ext. 6733
F +86 21 6288 0818

E-mail

sfs.info@sabic-ip.com

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of SABIC Holding Europe BV
* Trademarks of SABIC Innovative Plastics IP BV
© Copyright 2011. All rights reserved.