

## Description

Lexan\* SLX 11010 film is a clear polish film of 10 to 30 mil thickness that may be used alone or in a back molded configuration to provide exceptional weathering, good chemical and scratch resistance and outstanding aesthetics for a wide variety of applications in automotive, telecommunications and outdoor vehicles. It can be printed either first or second surface and retains good aesthetics and performance, even after significant outdoor exposure. Lexan SLX 11A13 film is a polish matte version (4 to 20mil) that exhibits the same performance, except for optical clarity and haze.

## Typical Property Values ♦

Property	ASTM Test Method	Units (USCS)	Value	ISO Test	Method Units (SI)	Value
<b>Mechanical</b>						
Tensile Strength @ Yield	ASTM D882	psi	12100	ISO 527	MPa	75.4
Ultimate	ASTM D882	psi	12600	ISO 527	MPa	85.7
Tensile Modulus	ASTM D882	psi	367000	ISO 527	MPa	2530
Tensile Elongation at Break	ASTM D882	%	82	ISO 527	%	74
Tear Strength Initiation	ASTM D1004	lb/mil	1.73		kN/m	245
Propogation	ASTM D1922	g/mil	18		g/mil	10-20
<b>Thermal</b>						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft <sup>2</sup> /°F/in	1.35		W/m <sup>0</sup> K	0.2
Coefficient of Thermal Expansion	ASTM E831	(x10 <sup>-5</sup> /°F)	3.2	ISO 11359	(x10 <sup>-5</sup> /°C)	5.8
Specific Heat @ 40 °F (4 °C)	ASTM E1269	Btu/lb/°F	0.24		KJ/Kg-°C	1
Glass Transition Temperature	ASTM D3417/D3418	°F	279	ISO 11357	°C	137
Vicat Softening Temperature, B	ASTM 1525-00 Modified	°F	290		°C	144
Heat Deflection Temp. by TMA at 1.8 MPa		°F	252	ISO 75 Modified	°C	122
<b>Physical</b>						
Specific Gravity	ASTM D792		1.26	ISO 1183	kg/m <sup>3</sup>	1260
Water Absorption, 24 hrs.	ASTM D570	% change	0.35	ISO 62	% change	0.35
Pencil hardness	ASTM D3363	-	HB			
Taber Abrasion	ASTM D1044	delta Haze, 50 cycles	19			
<b>Optical</b>						
Refractive Index @ 77 °F (25 °C)	ASTM D542A	-	1.6			
Light Transmission	ASTM D1003	%	88			
Yellowness Index	ASTM D1925	%	3			
Haze	ASTM D1003	%	<1			
Gloss over Flat Black min/max @ 60°	ASTM D523-60	-	176			
<b>Flammability</b>						
Non UL flame test, 10 mil monolayer	SABIC		V2			

♦ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC Innovative Plastics representative

\* Trademark of SABIC Innovative Plastics IP BV



\* Trademark of SABIC Innovative Plastics IP BV

Americas:  
SABIC Innovative Plastics  
Specialty Film & Sheet  
One Plastics Avenue  
Pittsfield, MA 01201  
USA  
Tel. (1) (413) 448 5400  
Toll-free: 1-800-323-3783 ext. 3  
Fax. (1) (866) 420 0637

Europe:  
SABIC Innovative Plastics  
Specialty Film & Sheet  
Plasticslaan 1  
NL - 4612 PX Bergen op Zoom  
The Netherlands  
Tel. (31) (164) 29 3678  
Fax. (31) (164) 29 3272

Pacific:  
SABIC Innovative Plastics  
Specialty Film & Sheet  
1266 Nanjin Road (W)  
16<sup>th</sup> Floor, United Plaza  
200040 Shanghai, China  
Tel. (86) 21 62881088 ext. 6733  
Fax. (86) 21 6288 0818

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of SABIC Holding Europe BV

\* Trademark of SABIC Innovative Plastics IP BV