

EFR735-BK1005 Film  
Developmental Grade EXSPB75-BK1005

Product Datasheet

Description

EFR 735 is halogen-free flame retardant Polyphenylene Oxide film offering UL94 VTM-0 performance down to 0.006" (152 microns) and excellent temperature performance to meet the requirements in a wide range of electrical, electronic and transportation applications. EFR 735 film has outstanding dielectric strength, ease of fabrication such as thermoforming, embossing, clean-edge die-cutting, score and bend. Gauges available are 6mil, 10mil, 17mil and 25mil in Matte/Velvet texture finish.

Typical Property Values ♦

Property	ASTM Test Method	Units (USCS)	Value	ISO Test Method	Units (SI)	Value
<b>Mechanical</b>						
Tensile Strength @ Yield	ASTM D882	psi	9000	ISO 527	Mpa	62
Ultimate	ASTM D882	psi	7600	ISO 527	Mpa	54.6
Tensile Modulus	ASTM D882	psi	294000	ISO 527	Mpa	2030
Tensile Elongation at Break	ASTM D882	%	12	ISO 527	%	12
<b>Tear Strength</b>						
Initiation 0.006"	ASTM D1004	lbf/mil	1.32	-	N/mm	232
Initiation 0.010"	ASTM D1004	lbf/mil	1.35	-	N/mm	236
Initiation 0.017"	ASTM D1004	lbf/mil	1.49	-	N/mm	262
Initiation 0.025"	ASTM D1004	lbf/mil	1.52	-	N/mm	265
Propagation 0.006"	ASTM D1922	g/mil	22	-	N/mm	8.5
Propagation 0.010"	ASTM D1922	g/mil	29	-	N/mm	11.1
Propagation 0.017"	ASTM D1922	g/mil	35	-	N/mm	13.7
Propagation 0.025"	ASTM D1922	g/mil	36	-	N/mm	13.9
<b>Puncture Resistance (Dynatup)</b>						
Total Energy	ASTM D3763	ft-lb/inch	186	-	J/mm	9.9
<b>Fold Endurance (MIT)</b>						
0.006" (0.152mm)	ASTM D2176	double folds	>1000	ISO 5626	double folds	>1000
0.010" (0.250mm)	ASTM D2176	double folds	>80	ISO 5626	double folds	>80
0.017" (0.432mm)	ASTM D2176	double folds	10	ISO 5626	double folds	10
0.025" (0.635mm)	ASTM D2176	double folds	7	ISO 5626	double folds	7
<b>Thermal</b>						
CTE 0-80 deg C, in flow	ASTM E831	1/°F	4.4x10 <sup>-5</sup>	ISO 11359	1/°C	8x10 <sup>-5</sup>
CTE 0-80 deg C, cross flow	ASTM E831	1/°F	4.4x10 <sup>-5</sup>	ISO 11359	1/°C	8x10 <sup>-5</sup>
Vicat Softening Temp, Rate B/50		°F	282/309	ISO 306	°C	162
Glass Transition Temperature	ASTM D3417	°F	342	ISO 11357	°C	172
Shrinkage 130°C 30 min TD	ASTM D1204	%	0.08		%	0.08
Shrinkage 130°C 30 min MD	ASTM D1204	%	0.15		%	0.15
<b>Physical</b>						
Density	ASTM D792	slug/ft <sup>3</sup>	2.1	ISO 1183	kg/m <sup>3</sup>	1088
<b>Water Absorption</b>						
23°C, 50% Relative Humidity, 24hrs	ASTM D570	% change	0.07	ISO 62	% change	0.07
24hrs water immersion	ASTM D570	% change	0.4	ISO 62	% change	0.4
<b>Electrical</b>						
<b>Dielectric Strength in oil, short time</b>						
@23°C, 0.006" (0.152mm)	ASTM D149-97a Method A	kV/mil	2.3	IEC 60243	kV/mm	90
@23°C, 0.010" (0.250mm)		kV/mil	1.8	IEC 60243	kV/mm	70
@23°C, 0.017" (0.432mm)		kV/mil	1.2	IEC 60243	kV/mm	47
@23°C, 0.025" (0.635mm)		kV/mil	1	IEC 60243	kV/mm	38
<b>Break Down Voltage in oil</b>						
@23°C, 0.006" (0.152mm)	ASTM D149-97a Method A	V	13500	IEC 60243	V	13500
@23°C, 0.010" (0.250mm)		V	18200	IEC 60243	V	18200
@23°C, 0.017" (0.432mm)		V	2100	IEC 60243	V	21000
@23°C, 0.025" (0.635mm)		V	24600	IEC 60243	V	24600
Dielectric Constant @ 1,000,000Hz	ASTM D150	-	2.75	IEC 60250	-	2.75
Dissipation Factor @ 1MHz	ASTM D150	-	0.0028	IEC 60250	-	0.0028

♦ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC Innovative Plastics, Specialty Film & Sheet representative or the Quality Services Department. Reported values are based on 0.250 mm (0.010" ) thickness film unless otherwise noted.

**EFR735-BK1005 Film**  
Developmental Grade EXSPB75-BK1005

**Product Datasheet**

**Manufacturing Specifications**

Nominal Gauge Ranges	Min./Max Limit of Nominal
0.006" (0.152 mm)	+/- 10%
0.010-0.017" (0.250-0.4318mm)	+/-5%
0.020-0.030" (0.500- 0.750 mm)	+/-3%

**UL Flammability Rating / Performance Levels**

Thickness	Rating
0.006"	UL94 - VTM 0
0.010"-0.017"	UL94 - V 0
File number	E255088

Americas:  
SABIC Innovative Plastics  
Specialty Film & Sheet  
One Plastics Avenue  
Pittsfield, MA 01201  
USA  
Tel. (1) (413) 448 7110  
Fax. (1) (413) 448 5573

Europe:  
SABIC Innovative Plastics  
Specialty Film & Sheet  
Plasticslaan 1  
NL - 4612 PX Bergen op Zoom  
The Netherlands  
Tel. (31) (164) 292911  
Fax. (31) (164) 292940

Pacific:  
SABIC Innovative Plastics  
Specialty Film & Sheet  
1468 Nanjin Road (W)  
26<sup>th</sup> Floor, United Plaza  
200040 Shanghai, China  
Tel. (86) 21 3222 4500  
Fax. (86) 21 6289 8998

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of SABIC Holding Europe BV