

Material Safety Data Sheet



Polymer name: Rigid PVC Films

1.	Substance/Preparation and Company Identification Polymer: Rigid PVC (Vinyl) films Company name: Klöckner Pentaplast of America, Inc. 3585 Klöckner Road, P.O. Box 500 Gordonsville, VA 22942 USA Information about material/preparation: Phone: +1.540.832.3600 (identical with emergency information)
2.	Composition/Information on Ingredients Chemical description: Polyvinyl Chloride Dangerous components: None
3.	Hazard Identification Not applicable
4.	Emergency and First Aid Procedures (only necessary when handled without care) Inhalation: If PVC decomposes due to overheating or in contact with fire, remove effected persons to fresh air. In case of irritation of respiratory system or if feeling unwell after prolonged exposure, seek medical attention. Skin contact: If contact with hot (melt) product occurs, wash with plenty of water. Treat as for a thermal burn. Eye contact: After contact with hot (melt) product, immediately flush eyes with water for at least several minutes. Seek medical attention. Ingestion: To avoid irritation, seek medical advice. Advice for the doctor: After inhalation of decomposed products, treat symptoms (decontamination, vital functions). If necessary, take action against irritation of the mucous membranes with HCl.

The statements contained herein are for informational purposes only and are true and accurate to the best of our scientific and technical knowledge. This information does not constitute a guarantee or warranty, express or implied, nor does it establish a legally valid contractual relationship. It is the customer's responsibility to determine the suitability of this product for the customer's intended use, and Klöckner Pentaplast does not assume any liability for the customer's use of this product or the information contained herein.
Revision: 7/2013

Klöckner Pentaplast GmbH
P.O. Box 1165, 56401 Montabaur,
Industriestrasse 3-5, 56412 Heiligenroth, Germany
Phone: +49.2602.915.0, Fax: +49.2602.915.297
kpinfo@kpfilms.com, kpfilms.com

Klöckner Pentaplast of America, Inc.
P.O. Box 500, 3585 Klöckner Road,
Gordonsville, Virginia, USA 22942
Phone: +1.540.832.3600, Fax: +1.540.832.5656
kpinfo@kpfilms.com, kpfilms.com

Klöckner Pentaplast (Suzhou) Specialty Materials Co., Ltd
12 Xia Sheng Road, Suzhou Industrial Park
Suzhou 215126, P.R. China
Phone: +86.(0)512.6260 9991, Fax +86.(0)512.6260 9992
kpinfo-CN@kpfilms.com, kpfilms.com

5.	<p>Fire Fighting Procedures</p> <p>Suitable extinguishing media: Water spray, powder, carbon dioxide</p> <p>Unsuitable extinguishing media: None</p> <p>Burning may release: Carbon Dioxide (CO₂) Water vapour (H₂O) Hydrochloric gas (HCl)</p> <p>If the burning material cannot get enough air, release of carbon monoxide, soot, and other gases and vapors is possible.</p> <p>Special protective equipment: If necessary, use air-bottled or air circulating apparatus for fire fighters.</p> <p>Further information: PVC-U does not burn without a slave flame (self extinguishing). Observe local regulations when contaminated water and burning waste are removed.</p>
6.	<p>Spill or Leak Procedures</p> <p>Personal precautions: Not applicable</p> <p>Environmental precautions: Not applicable</p> <p>Methods of cleaning: Pick up by mechanical means for disposal or reuse</p>
7.	<p>Handling and Storage Precautions</p> <p>Handling: Avoid overheating the material, it decomposes to gaseous components (see also 5.). Thermal degradation does not occur at low temperatures, but becomes faster at higher temperatures.</p> <p>Decomposition: >150°C (long-term contact) >200°C (short-term contact/i.e., warm forming)</p> <p>It is advisable to install low exhaust ventilation in the vicinity of processing machines in all areas where melt or high-temperature processing is carried out. (Germany should observe TRGS 402)</p> <p>Fire and Explosion Protection: Take precautionary measures against static discharge (i.e., using proper grounding techniques) when handling rolls or sheets in dry rooms (especially to avoid harm to people). According to VDI 2263, page 1, paragraph 2.1.2.3 (dd May 1990), PVC is not dust explosive as delivered by Klöckner Pentaplast.</p> <p>Storage: Take precautionary measures to avoid fire hazard. Store in normal room conditions without direct exposure to sunlight.</p>

The statements contained herein are for informational purposes only and are true and accurate to the best of our scientific and technical knowledge. This information does not constitute a guarantee or warranty, express or implied, nor does it establish a legally valid contractual relationship. It is the customer's responsibility to determine the suitability of this product for the customer's intended use, and Klöckner Pentaplast does not assume any liability for the customer's use of this product or the information contained herein.
Revision: 7/2013

Klöckner Pentaplast GmbH
P.O. Box 1165, 56401 Montabaur,
Industriestrasse 3-5, 56412 Heiligenroth, Germany
Phone: +49.2602.915.0, Fax: +49.2602.915.297
kpinfo@kpfilms.com, kpfilms.com

Klöckner Pentaplast of America, Inc.
P.O. Box 500, 3585 Klöckner Road,
Gordonsville, Virginia, USA 22942
Phone: +1.540.832.3600, Fax: +1.540.832.5656
kpinfo@kpfilms.com, kpfilms.com

Klöckner Pentaplast (Suzhou) Specialty Materials Co., Ltd
12 Xia Sheng Road, Suzhou Industrial Park
Suzhou 215126, P.R. China
Phone: +86.(0)512.6260 9991, Fax +86.(0)512.6260 9992
kpinfo-CN@kpfilms.com, kpfilms.com

<p>8.</p>	<p>Exposure Control/Personal Protection</p> <p>Additional advice for design of machines: See item 7</p> <p>Components with limits to be observed (depending upon work station): PVC is recognized as safe. However, it may contain trace amounts of: Vinylchloride monomer VCM, CAS-No. 75-01-4, EINECS-No. 2008310 MAK-Value: 2ppm (5 mg/m³) (Germany as TRK-value acc. to TRGS 102)</p> <p>For Penta brand films, a VCM value of ≤0,5 ppm is guaranteed. Given the special precautions mentioned under "7. Handling," these traces present no toxic risk to the processing personnel.</p> <p>Protection: Gloves should be worn when handling hot material. Safety glasses are normally recommended for all industrial workplaces when handling hot material.</p>
<p>9.</p>	<p>Physical and Chemical Properties</p> <p>Form: Mono films</p> <p>Color: From clear to black as required</p> <p>Smell: Odorless under normal conditions, melt material has a specific odor know as "plastic."</p> <p>Change of state: Softening temperature (DIN EN ISO 306): 60-90°C Glass transition temperature: approx 80°C Ignition temperature: see point 7</p> <p>Solubility of PVC: Density (DIN EN ISO 1183-2): 1,25-1,45 g/cm³ Soluble in: tetrahydrofuran and cyclohexanone Partly soluble in: different aromatic hydrocarbons Not soluble in: water, diluted acids and bases</p> <p>Fire supporting properties: PVC products are not easily combustible without a slave flame source</p>
<p>10.</p>	<p>Stability and Reactivity</p> <p>Conditions to avoid: Thermal degradation by overheating (see 7.)</p>

The statements contained herein are for informational purposes only and are true and accurate to the best of our scientific and technical knowledge. This information does not constitute a guarantee or warranty, express or implied, nor does it establish a legally valid contractual relationship. It is the customer's responsibility to determine the suitability of this product for the customer's intended use, and Klöckner Pentaplast does not assume any liability for the customer's use of this product or the information contained herein.
Revision: 7/2013

Klöckner Pentaplast GmbH
P.O. Box 1165, 56401 Montabaur,
Industriestrasse 3-5, 56412 Heiligenroth, Germany
Phone: +49.2602.915.0, Fax: +49.2602.915.297
kpinfo@kpfilms.com, kpfilms.com

Klöckner Pentaplast of America, Inc.
P.O. Box 500, 3585 Klöckner Road,
Gordonsville, Virginia, USA 22942
Phone: +1.540.832.3600, Fax: +1.540.832.5656
kpinfo@kpfilms.com, kpfilms.com

Klöckner Pentaplast (Suzhou) Specialty Materials Co., Ltd
12 Xia Sheng Road, Suzhou Industrial Park
Suzhou 215126, P.R. China
Phone: +86.(0)512.6260 9991, Fax +86.(0)512.6260 9992
kpinfo-CN@kpfilms.com, kpfilms.com

11.	<p>Information about Toxicity</p> <p>PVC is recognized as safe and biologically inert.</p> <p>Klöckner Pentaplast certifies that its rigid film and sheet product complies with the most recent package requirements for heavy metals of the Toxic Packaging Clearing House (TPCH, formerly CONEG) legislation and the latest March 9, 2005, requirements of the Directive 2013/2/EU, as well as the Commission Decision of 2011/534/EU amending the Directive 2002/95/EC [RoHS-Reduction of Hazardous Substances] in their actual valid version.</p>
12.	<p>Ecological Information</p> <p>PVC is not soluble in water (WKG 0, by supplier self declaration); PVC is harmless in contacts with fish and bacteria. In a water treatment plant, PVC can be separated mechanically.</p>
13.	<p>Disposal Considerations</p> <p>Klöckner Pentaplast guarantees the recycling of customers' material (=100% kp material). Recycling of printed or other used material is also possible, but this depends on the degree of impurities.</p> <p>Untaminated material is normally used as material for recycling, but can also be treated as household or incineration waste in accordance with local regulations.</p> <p>European Waste-Catalogue: code 200139 for plastics.</p> <p>Klöckner Pentaplast certifies that its rigid film and sheet product complies to the European Packaging Directive EU 94/62, as well as its amendments.</p>
14.	<p>Transport</p> <p>No hazardous material according to transport regulations (ADR, RID, ADNR, IMDG, IATA).</p>
15.	<p>Regulatory Information</p> <p>EEC labelling acc. Regulation (EC) 1272/2008 (Directive 67/548/EEC) as well as its actual valid amendments: Not applicable</p> <p>National legislation acc. to § 4a GefStoffV: Not applicable</p> <p>NB: This means PVC films are not considered hazardous materials.</p>
16.	<p>Further Information</p> <p>Klöckner Pentaplast rigid films and sheet products do not contain any Ozone depleting substances, including those listed in the 1990 Clean Air Act Amendments.</p> <p>The information and recommendations contained herein are based upon present data believed to be correct. However, no guarantee or warranty of any kind expressed or implied is made with respect to the information contained herein.</p>

The statements contained herein are for informational purposes only and are true and accurate to the best of our scientific and technical knowledge. This information does not constitute a guarantee or warranty, express or implied, nor does it establish a legally valid contractual relationship. It is the customer's responsibility to determine the suitability of this product for the customer's intended use, and Klöckner Pentaplast does not assume any liability for the customer's use of this product or the information contained herein.
Revision: 7/2013

Klöckner Pentaplast GmbH
P.O. Box 1165, 56401 Montabaur,
Industriestrasse 3-5, 56412 Heiligenroth, Germany
Phone: +49.2602.915.0, Fax: +49.2602.915.297
kpinfo@kpfilms.com, kpfilms.com

Klöckner Pentaplast of America, Inc.
P.O. Box 500, 3585 Klöckner Road,
Gordonsville, Virginia, USA 22942
Phone: +1.540.832.3600, Fax: +1.540.832.5656
kpinfo@kpfilms.com, kpfilms.com

Klöckner Pentaplast (Suzhou) Specialty Materials Co., Ltd
12 Xia Sheng Road, Suzhou Industrial Park
Suzhou 215126, P.R. China
Phone: +86.(0)512.6260 9991, Fax +86.(0)512.6260 9992
kpinfo-CN@kpfilms.com, kpfilms.com